



ADHERE RTG Sanded Grout

DESCRIPTION:

ADHERE RTG Sanded Grout is a Tile grout consisting of a carefully blended mix of Portland Cement, graded aggregates and color-fast pigments. Designed for use with ADHERE TGL Grout admix for optimum performance. It is suitable for non-absorbent & vitreous type tiles for grout joints 3-10mm. The grout with the grout admix provides a grout joint that is dense, hard and durable, color fast and less water absorbent. Available in a full range of architectural colors. Adhere RTG Wide is cementitious tile joint filler for wider joints of non porous, pavement tiles. It fills wider gap without cracking & shrinking when mixed with Adhere RTG Wide Additive. It is a factory prepared mix of Portland cement, aggregates & pigments which provide washable & long lasting color.

Application

Ideal for use with Ceramic tile, Vitrified tile, brick etc. When grouting glazed wall tile or marble use ADHERE CTG Grout.

Advantages

- color-fast
- weather resistant
- easy maintenance
- non-shrinking
- non-cracking
- Easy application and clean up
- No wet curing required when with latex
- Provides Waterproofing

Method of Application

- Add 5 parts of Adhere RTG wide to 1 part of Adhere RTG wide additive by weight or 3 to 4 part of Adhere RTG wide to 1 part of water. Mix to Smooth Consistency
- Apply the paste to the tile joints with a sponge / squeeze trowel.
- For filling the joints, fill the gaps by spreading filler paste in the space between the tiles with the help of rubber trowel in such a way that the entire area of joint / gap are filled with the joint filler paste. Press light pressure of finger in such a way that it creates "U" shape in two tiles joints to form channel to pass water through it.
- Remove surplus Adhere RTG wide with a damp sponge
- Allow 24 hours for the filling to dry. Then polish the tile with a clean, dry Cloth.

Note - Adhere RTG wide is recommended to mix with Adhere RTG wide additive to improve the performance with respect to colour fastness. Flexibility, waterproof & abrasion resistance.

Limitation

- For absorbent tile and marble use ADHERE CTG Un-Sanded Grout.
- Do not use where chemical resistance is required. Use ADHERE ETG Grout.
- Do not use acid to clean colored grout joints.
- For better color retention and water resistance, use ADHERE TGL Grout admix
- mortars and grouts for ceramic tile, pavers, brick and stone are not replacements for waterproof membranes. When a waterproof membrane is required, use a ADHERE Flex Waterproof Membrane.

Note:

Whilst any information and / or specification contained herein is to the best of our knowledge true and accurate, no warranty is given or implied in connection with any recommendation or suggestions made by us, our representatives, agents or distributors as the conditions of use of any labour involved are beyond our control.

INSTALLATION

Surface Preparation

Before starting to grout remove spacers and debris in grout joints and remove dust and dirt using a wet sponge. Do not leave water standing in joints.

Mixing

GROUT ADMIX thoroughly before use.

Use approximately 2ltrs of ADHERE TGL for 10 kg of ADHERE RTG powder. Place ADHERE TGL in a clean mixing container and add grout powder slowly. Mix by hand or with a slow speed mixer to a smooth stiff consistency.

Application

Dampen tile surface with water. Spread with a sharp, firm rubber grout float. Work the grout paste into the joints until completely filled. Use diagonal strokes to pack the joints. Insure that joint is filled and grout is not just sitting on top (i.e. "bridging the joint")

Note: For fuller flush joints sprinkle a thin layer of dry grout powder over surface immediately after grouting. When grout darkens over joint, buff with burlap, carpet remnant or cotton rag to pack joint and clean face of tile.

Cleaning

Grout Primary Cleaning - Remove excess grout from the face of the tiles with the edge of the grout float. Hold the float at a 90° angle and pull it at a 45° angle diagonally across the joints and tile to avoid pulling out the material
Grout Secondary Cleaning - Remove remaining grout with a damp sponge (not wet) or a damp towel. Work diagonally to the joints. Allow to dry. When the grout joints are firm polish the surface with a coarse nylon pad or coarse cloth and minimal water.

Note: Use caution when polishing soft glazed tiles or polished stone. Selecting Other Grout Materials ADHERE ETG has grouting materials designed for every use. For installations that require high strength and chemical resistance choose These products are ideal for installations where a stain free colorfast grout is desired.

Areas of Application: For filling wider tile joints of pavement / outdoor & non porous tiles up to 12 mm

Packages: 25Kgs (Powder 20kg + Liquid 5Kg)

